



NYMCO S.p.A. – OFFICES / PLANT: Via Carlo Magni, 1 – 21049 Tradate (VA) – Tel. +39 0331 85351 – Fax +39 0331 853581

[www.nymco.com](http://www.nymco.com)

[sales@nymco.com](mailto:sales@nymco.com)

## **PLASTICISERS RANGE**

<b>Product</b>	<b>Chemical description</b>	<b>Colour (APHA SCALE)</b>	<b>Water content (%KF)</b>	<b>Saponification value (mgKOH/g)</b>	<b>Hydroxyl value (mgKOH/g)</b>	<b>Acid value (mgKOH/g)</b>	<b>ESTER CONTENT WT%</b>	<b>Application</b>
Nymcoplast BCF	BUTIL CARBITOLO FORMALE	250	0.2	N.D.	18 MAX	0.3 MAX	N.D.	RUBBER
Nymcoplast DBS	DIBUTILSEBACATO	100	0.3	345 – 370	1.5 MAX	0.3 MAX	N.D.	PVC, RUBBER, INKS
Nymcoplast DIBA	DIISOBUTILADIPATO	100	0.3	425 – 445	N.D.	0.3 MAX	N.D.	PVC
Nymcoplast DA	DIISOPROPIL ADIPATO	60	0.3	465 - 500	N.D.	0.5 MAX	98 MIN	PERSONAL CARE
Nymcoplast DOA	DIOTTILADIPATO	100	0.3	CIRCA 300	1.5 MAX	0.3	N.D.	PVC, RUBBER, INKS
Nymcoplast DOS	DIOTTILSEBACATO	100	0.3	260 - 268	N.D.	0.3	N.D.	PVC, RUBBER
Nymcoplast EHA	ETILESILACETATO	30	0.1	N.D.	N.D.	0.1	98 MIN	PAINT
Nymcoplast TBC	TRIBUTILCITRATO	50	0.25	450 – 500	N.D.	0.2	98 MIN	PAINT, RUBBER
Nymcoplast 6	BUTILCARBITOLO ADIPATO	150	0.5	N.D.	N.D.	2 MAX	N.D.	RUBBER
Nymcoplast 9	DIBUTOSSIETOSIETIL ADIPATO	500	0,2	185 – 210	N.D.	0,15 MAX	N.D.	RUBBER
Nymcoplast APGD-MV	POLIGLICOLEADIPATO	100	N.D.	N.D.	N.D.	1 MAX	N.D.	PVC
Nymcoplast APGD-LV	POLIGLICOLEADIPATO	100	N.D.	N.D.	N.D.	1 MAX	N.D.	PVC



<b>Product</b>	<b>Chemical description</b>	<b>Colour (APHA SCALE)</b>	<b>Water content (%KF)</b>	<b>Saponification value (mgKOH/g)</b>	<b>Hydroxyl value (mgKOH/g)</b>	<b>Acid value (mgKOH/g)</b>	<b>ESTER CONTENT WT%</b>	<b>Application</b>
Nymcoplast ELA	ETILE LATTATO	50	0,3	N.D.	N.D.	N.D.	98	INKS, PAINTS
Nymcoplast 50	DEG/DPG GLICOLE DIBENZOATE	100	0.1	N.D.	N.D.	0.1	98	PVC, LATEX
Nymcoplast 100 G	DIPROPILENGLICOLE DIBENZOATO	100	0.1	N.D.	15 MAX	0.1	98 MIN	PVC, LATEX
Nymcoplast 150	DIETILENGLICOLE DIBENZOATE	100	0.1	345 - 365	15 MAX	0.1	98 MIN	PVC, LATEX
Nymcoplast 102	TRIETILENGLICOLE DI CAPRIL/CAPRILATE	60	0,1	258 – 270	N.D.	0,09 MAX	N.D.	RUBBER
Nymcoplast 257	NEOPENTILGLICOLE DIEPTANOATO	40	0,1	330 – 355	N.D.	0,5 MAX	N.D.	PVC,LATEX
Nymcoplast AMG	ACETIL MONOGLICERIDE	100	0,1	N.D.	20 MAX	3 MAX	N.D.	PVC

**NYMCO S.p.A. – OFFICES / PLANT:** Via Carlo Magni, 1 – 21049 Tradate (VA) – Tel. +39 0331 85351 – Fax +39 0331 853581

[www.nymco.com](http://www.nymco.com)

[sales@nymco.com](mailto:sales@nymco.com)